

Nutrition Geotextile Test Report

Product Name	Nutrition geotextile	Specification	180gsm	
Sample from	Non-Woven Geo-textile workshop			
Test Type	Leaving Factory Test	Test Date	Jan.05, 2019	
Content of Test				
No.	Items	Unit	Test Value	Notes
1	Weight	g/sqm	189	
2	Weight Variation	%	5	
3	Thickness	mm	2.3	
4	Tensile Strength	KN/m	MD 2.1 CD 2.7	MD and TD
5	Elongation	%	MD 132 CD 127	MD and TD
6	CBR	N	690	
7	Sieve Size O ₉₀	mm	1.8	
Not				



Inspector: Du Meng

Checker: Wang Jing

Continuous Filament spunbond needle punched Geotextile Test Report

Product Name	Continuous filament spunbond needle punched Geotextile Test Report	Specification	500gsm		
Sample from	Non-Woven Geo-textile workshop				
Test Type	Leaving Factory Test	Test Date	Dec.16, 2015		
Content of Test					
No.	Items	Unit	Test Value	Standard Value	Notes
1	Weight	g/sqm	504	500	
2	Weight Variation	%	0.8	-5	
3	Thickness	mm	4.69	3.4	
4	Tensile Strength	N/5cm	MD 2120	1250	MD and TD
			CD 1875	1250	
5	Elongation	%	MD 62.6	40-80	MD and TD
			CD 64.6	40-80	
6	Tear Strength	N	MD 990	700	MD and TD
			CD 906	700	
General Quality	In Accordance With Applied Standard: GB/T17639-1998 Qualified Product				

Inspector: Du Meng

Checker: Wang Jing